

BLANK PAGE



Indian Standard

SPECIFICATION FOR GERMINATION PAPER

(First Revision)

First Reprint SEPTEMBER 1992

UDC 631.547.1:676.252.333

© Copyright 1988

BUREAU OF INDIAN STA'NDARDS

MANAK BHAVAN. 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

Indian Standard SPECIFICATION FOR GERMINATION PAPER (First Revision)

Seed Processing and Technology Sectional Committee, AFDC 62

Chairman

SHRI V. P. SINGH

Representing

National Seeds Corporation Ltd, New Delhi; and Central Seeds Committee (Ministry of Agriculture), New Delhi

Members

Shri N. S. Tanwar (Alternate to Central Shri V. P. Singh) Agr Dr P. K. Agrawai. Indian

DR M. AHLUWALIA
SHRI M. M. VERMA (Alternate)

DR S. P. SINGH (Alternate) SHRI D. J. K. CORNELIUS DIRECTOR

SHRI S. S. BARATHOKEY

DR R. P. KACHRU

DR NAWAB ALI (Alternate) Shri E. M. Kharde

SHRI I. NICHOLAS SHRI S. B. PANDYA Central Seeds Committee (Ministry of

Agriculture), New Delhi Indian Agricultural Research Institute (ICAR), New Delhi

Central Seed Testing Laboratory, New Delhi

UP Seeds and Tarai Development Corporation Ltd, Pant Nagar

Plantek Services Pvt Ltd, Madras Maharashtra State Seed Certification Agency, Pune

Central Institute of Agricultural Engineering (ICAR), Bhopal

Maharashtra Hybrid Seeds Company Limited,

Maharashtra State Seeds Corporation Ltd, Akola India Crop Improvement and Seed Producers' Association, New Delhi

SHRI SHRIKANT GUPTA (Alternate I)
SHRI ANIL KUMAR MISHRA (Alternate II)

SHRI SHIRISH S. PANDYA SHRI V. A. PATIL

Krishiseva, Ahmedabad

Northern Region Farm Machinery Training and Testing Institute (Ministry of Agriculture), Hissar

SHRI R. TIWARI (Alternate)

(Continued on page 2)

Copyright 1988

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page '1)

Members

DR RAJINDER SINGH SHRI P. c. GROVER (Alternate)

SHRI K. NAGESWARA Rao

REPRESENTATIVE

SHRISAN JREV SAGAR SHRI M. K. GOYAL (Alternate)

DR R. P. SAXENA

DE S. P. SHARMA SHRI V. SUBRAMANIAM Corporation Limited, Hyderabad

The Andhra Pradesh State Seeds Development West Bengal State Seed Corporation Limited,

Calcutta

OSAW Agro Industries, Ambala Cantt

Representing

Panjab Agricultural University, Ludhinna

University of Agriculture and Technology, Pant Nagar

Indian Society of Seed Technology, New Delhi Department of Agriculture, Government of Tamil

Nadu, Madras

SHRIP. A. VIBHWANATHAN (Alternate) Shri V. S. Verma

UP State Seed Certification Agency, Lucknow

SHRI J. K. S. SIWAL (Alternate) SHRI T. PURNANANDAM,

Director (Agri & Food)

Director General, BIS (Ex-officio Member)

Secretary

SHRI R. N. SHARMA Joint Director (Agri & Food), BIS

Indian Standard SPECIFICATION FOR GERMINATION PAPER (First Revision)

O. FOREWORD

- 0.1 This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards on 17 August 1987, after the draft finalized the Seed Processing and Technology Sectional Committee had been approved by the Agricultural and Food Products Division Council.
- 0.2 Seed industry Kes made rapid advances in the country since the early 1960's. With the promulgation of Seeds Act 1966, it has become compulsory to attach truthful labels to each container of notified seed indicating the quality of seed being sold. It also provides for voluntary seed certification which requires seed to be tested before issuing the certificate. Increased emphasis is being placed on seed quality and correct labelling 0s all the seeds. To achieve the above, seed testing plays an indispensable role. The germination test forms a very important criteria for determining the quality of seed. For this test suitable substrata is required to be used to obtain accurate and reproducible results.
- 0.3 Paper forms one of the important substrata used in the germination test. In order to get reproducible results repeatedly, it is essential that the germination paper is 0 the desired quality. This standard covering the requirements for germination paper to be used for germination tests was prepared with a view to encourage production 0 the right quality 0 paper in the country. Based on the experience of implementation 0 the standard and to align with the requirements stipulated by International Seed Testing Association, a need was felt to revise the standard.
- 0.4 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS: 2-1960*. The number of significant places retained

^{*}Rules for rounding off numerical values (revised).

in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes the requirements and the methods of sampling and test for germination paper.

2. REQUIREMENTS

2.1 General

- **2.1.1** Formation The paper should have an open, porous formation and be free from defects or impurities that may affect its performance in service.
- 2.1.2 Cleanliness -The paper should be free of fungi or bacteria which might interfere with the growth or evaluation of germinating seedlings.
- 2.1.3 *Treatment* The paper should not be treated for the elimination of mould as this process might deposit chemicals in the paper which would suppress or kill disease organisms on the seeds.
- 2.1.4 **Pernicious Materials** -The paper shall not contain any impurities and toxic substances in such quantity as to cause injury to the roots of germinating seedlings when tested in accordance with the method prescribed in Appendix A.
- **2.1.5** Composition The paper shall be prepared from bleached chemical, wood, cotton or other purified vegetable cellulose.
- 2.1.6 Colour The paper may be white or coloured with a dye non-toxic to germinating seedlings.
- **2.1.7** Texture The texture of the paper should be such that the roots of germinating seedlings will grow on and not into the paper. A creped surface may be formed for filter and towel papers.
- 2.1.8 *Thickness When Wet* The total thickness of the paper when wet shall be not less than 2 mm.
- 2.2 **Physical Requirements** -The papers when measured at 50 percent relative humidity, shall meet the requirements as given in Table 1.

NOTE -When paper is measured at 65 percent relative humidity rather than 50 percent relative humidity, the basis mass is about 30 percent higher and the bursting strength is about 10 percent lower.

TABLE 1 REQUIREMENTS OF GERMINATION PAPERS
(Clause 2.2)

TYPE OF PAPER	CLASS OF PAPER	Basis* Mass g/m²	BURSTING STRENGTH, Min kN/m ²	Capillary Rise, Min mm	AOIDITY pH	Ash, Max Percent
(1)	(2)	(3)	(4)	(5)	(6)	(7)
Blotter	Light Medium Heavy	270 40 5 730	180 220 320	30 30 30	6.0 to 7.5 6.0 to 7.5 6.0 to 7.5	1.0 1.0
Filter	Light Medium Heavy	85 132 170	90 100 120	30 30 30	6:0 to 7:5 6:0 to 7:5 6:0 to 7:5	1'0 1'0 1'0
Towel	Light Medium Heavy	65 128 135	270 470 100	52 58 32	6.4 to 6.7 6.4 to 6.7 6.4 to 6.7	0'6 0·6 0·6

*Tolerance on basis mass of blotters is ± 5 percent, and for filter and towel ± 10 percent.

3. PACKING&ND MARKING

- **3.1 500** or **250** sheets, each measuring **455** x **275** mm with tolerance ± 2 mm on both dimensions may be wrapped in kraft paper and sealed with gummed paper tape or suitably packed as agreed to between the purchaser and the vendor.
- 3.2 Each package shall be marked' with the following information:
 - a) Description of the paper (towel or blotter or filter),
 - b) Class of paper (light, medium and heavy),
 - c) Plain or crepe,
 - d) Contents of the package (number of sheets),
 - e) Size in millimetres, and
 - f) Lot number.

3.2.1 The packages may also be marked with the Standard Mark.

Note—The use of the Standard Mark is governed by the provisions of the bureau of Indian Standards Act 1986 and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers, may be obtained from the Bureau of Indian Standards.

4. SAMPLING

4.1 Representative samples for tests shall be drawn as prescribed in 3 of IS: 1060 (Part 1)-1966*.

5. TESTS

- 5.1 Test for toxic material shall be conducted in accordance with the method given in Appendix A.
- 5.2 Test for basis mass shall be conducted in accordance with 6 of IS : 1060 (Part 1)-1966 $^{\bullet}.$

Note -The basis mass of crepe paper shall be taken on the basic material, that is, before creping is done.

- 5.3 Bursting strength shall be conducted in accordance with 12.5 of IS: 1060 (Part 1)-1966*.
- 5.4 The capillary rise shall be conducted in accordance with the method given in Appendix B.
- 5.5 Acidity and ash content shall be determined in accordance with $\bf 10$ and $\bf 11$ of IS : 1060 (Part 1)-1966* respectively.

APPENDIX A

(Clauses 2.1.4 and 5.1)

BIOLOGICAL TEST FOR TOXIC MATERIALS

A-I. PROCEDURE

A-l.1 In this test, comparison is made between germination papers of unknown quality and known acceptable quality. Pieces of paper are

^{*}Methods of sampling and test for paper and allied products, Part 1 (revised).

cut to size and placed in petri dishes or boxes. Use two thicknesses of the papers for each container. Moisten the papers with tap water, using only enough water to saturate the papers (no excess to pour off). The roots of seeds known to be sensitive to toxic paper used in test are seeds of onion or Brassica sp.

- A-l.2 Evaluate by comparing the development of the seedlings grown on unknown quality of paper and those grown on the 'check'. The evaluation of onions seedlings shall be made after 6 days and of *Brassica* seedlings after 3 days.
- A-1.3 Symptoms of root inhibition due to toxic paper are root tips shortened and sometimes **discoloured**, root hairs 'bunched', and sometimes plumules shortened.

APPENDIX B

(Clause **5.4**)

DETERMINATION OF CAPILLARY RISE

B-I. PROCEDURE

- **B-l.1** Cut from strips of paper each 10 mm wide, two in the machine direction of the paper and two in the cross-machine directions. Immerse each strip in distilled or de-ionized water to a depth of 20 mm at the end of the strip. At the end of two minutes, measure the height to which the water has risen in the strip, to the nearest 1 mm.
- B-l.2 **Report** Compute the average for the two strips cut in the machine direction, and the average for the two strips cut in the **cross**-machine direction. The lower of these two averages shall be taken as the result for the test.

BUREAU OF INDIAN STANDARDS

Headquarters:	
Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI	110002
Telephones: 331 01 31, 331 13 75 Telegrams: M (Common to	
Regional Offices:	Telephone
Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002	{331 01 31 }331 13 75
*Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola. CALCUTTA 700054	36 24 99
Northern: SCO 445-446, Sector 35-C, CHANDIGARH 160036	21843 3 16 41
	41 24 42
Southern: C. I. T. Campus, MADRAS 600113	₹41 25 19
†Western: Manakalaya, E9 MIDC, Marol, Andheri (East),	41 2916 8 32 92 95
BOMBAY 400093	
Branch Offices:	
'Pushpak'. Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001	2 63 48 1 2 83 49
‡Peenya Indust rial Area 1st Stage, Bangalore Tumkur Road BANGALORE 560058	
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003	667 16
Plot No. 82/83, Lewis Road. BHUBANESHWAR 751002 53/5, Ward No. 29, R.G. Barua Road, 5th Byelane,	5 36 27 3 31 77
GUWAHATI 781003	22 4002
5-8-56C L. N. Gupta Marg (Nampally Station Road), HYDERABAD 500001	23 1083
R14 Yudhister Marg. C Scheme, JAIPUR 302005	634 71 6 98 32
117/418 B Sarvodaya Nagar, KANPUR 208005	21 68 76 21 82 92
Patliputra Industrial Estate, PATNA 800013	6 23 05
T.C. No. 14/1 421. University P.O Palayam TRIVANDRUM 695035	∫6 21 04 ∫6 21 17
Inspection Offices (With Sale Point):	(02117
Pushpanjali, First Floor, 205-A West High Court Road,	2 5171
Shankar Nagar Square, NAGPUR 440010	

^{*}Sales Office in Calcutta is at 5 Chowringhrr Approach, P. O. Princep 27 66 00 Street. Calcutta 700072

Institution of Engineers (India) Building, 1332 Shivaji Nagar, 5 24 35

PUNE 411005

[†]Sales Office in Bombay is at Novelty Chambers, Grant Road, 89 65 26 Bombay 400007

[‡]Sales Office in Bangalore is at Unity Building, Narasimharaja Square, 22 36 71 Bangalore 560002